

ExxonMobil PP

PP5722 E1

General Purpose Extrusion Resin

Description

General purpose extrusion and injection molding resin.

Resin Properties	Test Method (based on)	Typical Values ¹	SI Units
Melt Flow Rate (230°C/2.16 kg)	ASTM D 1238	3.7 g/10 min	
Density	ASTM D 792	0.9 g/cm ³	

1. Values given are typical and should not be interpreted as specification.

FDA Status

For applications requiring FDA certification, please contact your ExxonMobil representative for compliance information.